





FUNI ACCIAIO ZINCATO A 6 TREFOLI ANIMA TESSILE

ZT 619 114 fili – 6x19+AT Crociata DX – Res. 1.770 N/mm ²	Ø FUNE	FILO EXT.	PESO	CARICO ROTTURA min.	
	mm.	mm.	Kg/m.	Kgf.	kN
	3	0,19	0,031	500	4,90
	4	0,26	0,055	890	8,73
	5	0,39	0,093	1.500	14,71
	6	0,47	0,134	2.250	22,06
	7	0,55	0,183	3.000	29,41
	8	0,63	0,238	3.820	37,45
	9	0,67	0,300	5.500	53,92
	10	0,74	0,370	6.500	63,73
	11	0,82	0,440	7.800	76,47
	12	0,89	0,530	9.300	91,18

ZT 619 R 114 fili – 6x19+AT Crociata DX – Res. 1.960 N/mm ²	Ø FUNE	FILO EXT.	PESO	CARICO ROTTURA min.	
	mm.	mm.	Kg/m.	Kgf.	kN
	5	0,39	0,093	1.800	17,65
	6	0,47	0,134	2.650	25,98
	7	0,55	0,183	3.420	33,53
	8	0,63	0,238	4.500	44,12
	9	0,67	0,300	5.800	56,86
	10	0,74	0,370	7.200	70,59
	11	0,82	0,440	8.800	86,27
	12	0,89	0,530	10.300	100,98

ZT 619 R-TR 114 fili – 6x19+AT – Trefoli Trafilati Crociata DX – Res. 2.160 N/mm ²	Ø FUNE	FILO EXT.	PESO	CARICO ROTTURA min.	
	mm.	mm.	Kg/m.	Kgf.	kN
	6	0,51	0,137	3.305	32,40
	6,3	0,55	0,170	3.720	36,47
	7	0,59	0,187	4.200	41,18
	7,3	0,64	0,225	4.750	46,57
	8	0,67	0,244	5.400	52,94
	9	0,76	0,309	7.000	68,63
	10	0,81	0,381	8.770	85,98
	11	0,87	0,461	10.500	102,94
	12	0,96	0,550	12.660	124,12

ZT 636 216 fili – 6x36+AT Crociata DX – Res. 1.770 N/mm ²	Ø FUNE	FILO EXT.	PESO	CARICO ROTTURA min.	
	mm.	mm.	Kg/m.	Kgf.	kN
	14	0,77	0,720	12.500	122,55
	16	0,89	0,950	16.350	160,29
	18	1,00	1,190	20.750	203,43
	20	1,10	1,470	25.700	251,96
	22	1,22	1,770	31.000	303,92
	26	1,44	2,420	43.300	424,51
	30	1,66	3,230	57.000	558,82